

## **VISTALITE SKY BLUE**

# Quietly neutral, with a hint of sheen

Vistalite subtly reflective color-enriched glass transmits generous levels of visible light and provides color neutrality, which amplifies and enriches the tint of the glass substrate underneath without a mirror-like appearance. More understated than traditional reflective glass, Vistalite glass is available in two distinct tints—Sky Blue and Euro Grey and rich-blue Pacifica. Vistalite glass can be combined with Solarban solar control low-e glass or SG 500 low-e glass to achieve light-to-solar gain ratios of as high as 1.66.

#### Vistalite Sky Blue: Performance Data For Monolithic Glass

Glass Configuration	UV	Visible Light			Solar Energy						U-Value W/M2K
Vistalite Sky Blue	Transmit- tance %	Transmit- tance %	Reflectance, Ext. %	Reflectance, Int. %	Transmit- tance %	Reflec- tance %	Absorp- tion %	Solar Factor EN410	SHGC	SC	EN 673
6 MM	18	44	16	29	33	17	50	0.51	0.50	0.58	5.7

<sup>-</sup> Performance data is based on representative samples of factory production. Actual values may vary slightly due to variations in the production process.
- Tabulated data is based on NRFC methodology using the LBL windows 5.2 software and where noted European methodology using WinDat WIS version 3.0.1 software.

## Vistalite Sky Blue:

### (Performance Data For IG Units 6mm/16mm Air Space/6mm)

	VLT	Visible Light Reflectance		sc	Solar Factor (G) En 410	U-value Imperial		U-value En 673 W/m²*k
		Ext.	Int.			Winter	Summer	
Trulite Clear	40%	17%	30%	0.45	0.39	2.80	2.70	2.70
SG 500 - Hard coat Low E#3	38%	16%	31%	0.39	0.34	1.90	1.80	1.80
Single silver low-E#3	35%	17%	28%	0.36	0.31	1.80	1.60	1.60

Data considers 16mm airspace and based on NFRC & EN 673. Other glass thickness is available. See literature or visit www.sphinxglass.com for additional values.

<sup>-</sup> SF = Solar Factor (EN410) also known as g-value